



|                           |   |                 |       |               |     |
|---------------------------|---|-----------------|-------|---------------|-----|
| Description               | P25-P. 75 $\mu$ matt clear 7 year polymeric PVC, permanent adhesive, 135gsm kraft liner<br><br>'P Series' 7 year polymeric for simple curved surfaces. Matt clear polymeric with a clear permanent adhesive on a kraft liner. Can be used as either a print vinyl or a matched matt laminate to our 'P Series' polymeric vinyls.  |                 |       |               |     |
| Key Features              | No adhesive milking when wet applied.<br>Available up to 1600mm wide.<br>Solvent, Latex and UV printable.<br>Can also be used as a matched laminate.<br>UVa block 67%<br>Splice free rolls.   |                 |       |               |     |
| Conversion                | Primarily for digital printing but can be CAD cut.<br>Prints should be left flat for at least 4 hours prior to cutting, lamination or application.  |                 |       |               |     |
| Precaution                | For application to flat and simple curved surfaces.   |                 |       |               |     |
| Application               | Dry or Wet application.   |                 |       |               |     |
| Compliance                | REACH and RoHS compliant  |                 |       |               |     |
| Fire Certification        | Self-extinguishing  |                 |       |               |     |
| Face Material             | Polymeric calendered PVC  |                 |       |               |     |
| Face Thickness            | 75 $\mu$ thick  |                 |       |               |     |
| Adhesive                  | Permanent clear UV polyacrylate   |                 |       |               |     |
| Adhesive weight           | Nominal 24gsm   |                 |       |               |     |
| Perceived Tack            | Medium Tack Permanent   |                 |       |               |     |
| Liner                     | 135gsm kraft liner  |                 |       |               |     |
| Dimensional stability     | Nominal 0.09mm  |                 |       |               |     |
| Conformability            | 2D Simple Curves  |                 |       |               |     |
| Optimal application temp  | +15 to 25°C   |                 |       |               |     |
| Min application temp      | +10°C   |                 |       |               |     |
| Max application temp      | +30°C   |                 |       |               |     |
| Intermittent service temp | -30 to 100°C  |                 |       |               |     |
| Shelf-life                | 2 year  |                 |       |               |     |
| Adhesive Data (Nominal)   | 180° Peel Adhesion N/25mm   |                 |       |               |     |
|                           |   | Stainless Steel | Glass | Polypropylene | MDF |
|                           | 20 min  | 19              | 21    | 2             | 5   |
|                           | 24 hour   | 23              | 25    | 5             | 9   |
|                           | 1 week  | 24              | 26    | 7             | 11  |
| Chemical Resistance       | The unprinted film can be wiped clean with water and diluted household detergents. Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.   |                 |       |               |     |
| Outdoor Durability        | 7 year unprinted Zone 1 (Northern Europe, North America) vertical exposure<br>3-4 year unprinted Zone 2 (S. Europe, Central & S. America, Asia Pacific) vertical exposure<br>2-3 year unprinted Zone 3 (Middle East, Africa & desert areas) vertical exposure   |                 |       |               |     |
| Important                 | The nominal values shown are based upon research and test methods on unprinted material and are provided without guarantee and do not constitute a warranty. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and correct application. For further information on the test methods used refer to <a href="http://www.nu-coat.com/testmethods">www.nu-coat.com/testmethods</a> . Nu-Coat Limited will not be liable for any indirect or consequential loss. |                 |       |               |     |