

# PHYSICAL TESTING REPORT



**Mactac UK**  
37 Tenter Road  
Moulton Park  
Northampton  
Northamptonshire  
NN3 6AY

FAO: Mr. Douglas Spencer

**Report of Tests on:** Self adhesive textured laminate

**Your Reference:** LUV 6300

**Lucideon Reference:** (154373)-24632

**Date Reported:** 15-Oct-2015

**Order Number:** PO 5012

**Date Logged:** 12-Oct-2015

**Date(s) of Test(s):** 14-Oct-2015 to 14-Oct-2015

**Inclined Platform Test for Slip Resistance In Shod Conditions**

DIN 51130:2010

No.	Operator 1 - Angle of Inclination	Operator 2 - Angle of Inclination
1	6.1	6.3
2	5.5	5.9
3	5.8	6.5

Description of Test Specimen(s): 2 textured laminate boards

Average of Six Shod Results (Corrected): 6.0 °

Category: R9

The critical angle at which a test person reaches the limit of safe walking on an inclined plane is used as a measure of slip resistance.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

**End of Test Report**

Mr Simon Hall  
Author