



TEST REPORT

Report No. : W2023-00102

Date: January 19, 2023

Applicant name : All Print Supplies Limited
Applicant address : /
Contact person : /
Sample description : The following sample(s) was/were submitted and identified on behalf of the client as
Item name : MESH300
Colour : /
Style No. : 1000*1000 12*12
Order No. : /
Composition : /
Other information : /
Date received : January 5, 2023
Test completed : January 19, 2023
Remark : /
Test details : Refer to the test details requested by the applicant on next page(s).

Test Chop

Approved by

Verified by

Prepared by



TEST REPORT

Report No. : W2023-00102

Date: January 19,2023

Test details requested by the applicant :

Fire behaviour(Method: DIN 4102-1:1998)

Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23 ± 2 °C, and a relative humidity of 50 ± 6 %.

Test results

“Brandschacht“ Test according to DIN 4102-1:1998

Exposed surface: The Front face

Results of “Brandschacht” Test (part 1)						
Line No.		Unit	Test Line assemblies No.			
			A	B	C	D
1	Specimen fixings according to DIN 4102 part 15, table	-	1			
2	Max. flame height above lower sample edge;	cm	30			
3	Time ¹⁾	s	1			
4	<u>Melting/burning through</u> Time ¹⁾	s	6			
5	<u>Back of specimen</u> Flaming/glowing, Time ¹⁾	s	1			
6	<u>Discolouring, Time ¹⁾</u>	s	1			
7	<u>Burning droplets</u> Begin 1)	s	Yes 1			
8	Amount		4			
9	Specimen material falling off in separate droplets		/			
9	Specimen material falling off continuously		/			
10	<u>Burning parts</u> Begin 1)	s	NO /			
11	Parts of sample falling off separately		/			
12	Parts of sample falling off continuously		/			
13	Duration of continued combustion on mesh base (max.)	s	NO			
14	<u>Burner flame impairment by dripping/falling material</u> Time ¹⁾	s	NO /			
15	<u>Premature ending of test</u> End of burning at specimen ¹⁾	s	/			
16	Time when test terminated (if applicable) ¹⁾	s	/			
17	<u>Burning after end of test</u> Duration	s	NO /			
18	Number of specimens		/			
19	Front of specimen		/			
20	Back of specimen		/			
21	Height of flame	cm	/			



TEST REPORT

Report No. : W2023-00102

Date: January 19,2023

Results of "Brandschacht" Test (part 2)					
Line No.	Unit	Test Line assemblies No.			
		A	B	C	D
	<u>Glowing after end of test</u>	NO			
22	Duration	s	/		
23	Number of specimens	/			
24	Front of specimen	/			
25	Back of specimen	/			
26	Top half of specimen	/			
27	Bottom half of specimen	/			
	<u>Residual length</u>				
28	Single results	cm	65	75	
			73	74	
29	Average of the single results	cm	72		
	<u>Smoke temperature</u>				
30	Max. of average	°C	136		
31	Time ¹⁾	s	250		

Note: 1)time from start of testing

2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Flame application: bottom edge ignition

Specimen No.		1	2	3	4	5
Reaching the measuring mark within 20 seconds	Warp	NO	NO	NO	NO	NO
	Weft	NO	NO	NO	NO	NO

Flame application: surface ignition

Specimen No.		1	2	3	4	5
Reaching the measuring mark within 20 seconds	Warp	NO	NO	NO	NO	NO
	Weft	NO	NO	NO	NO	NO

All timings are from start of testing

Criteria for classification for Class B1 (DIN 4102-1 Clause 6.1.2)

All materials, except flooring, may be classed as B1 materials if they met,

a) Pass DIN 4102-16 "brandschacht" test if

1) The mean value for the residual length of each specimen is at least 15 cm, and no individual values are lower than 0 cm;

2) The mean effluent temperature does not exceed 200°C in any test;

3) The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.

b) Pass DIN 4102-1 Clause 6.2.3 Ignitability Test if,

For each specimen, flaming doesn't reach the gage mark within 20s after flame application.

Conclusion:

The tested sample meets the low flammability requirements of class B1 of building materials



TEST REPORT

Report No. : W2023-00102

Date: January 19,2023

under DIN 4102-1:1998.

STATEMENTS:

This test report does not replace any mandatory certification of the product that may be required. The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

Remark: This item is only approved by CNAS.




TEST REPORT

Report No.: W2023-00102

Date: January 19, 2023

Sample Photo



***** End of Report *****